

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁶ : A61C 15/04, A61K 7/16</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/29257 (43) International Publication Date: 17 June 1999 (17.06.99)</p>
<p>(21) International Application Number: PCT/US98/26150 (22) International Filing Date: 9 December 1998 (09.12.98) (30) Priority Data: 60/069,187 10 December 1997 (10.12.97) US (71) Applicant (for all designated States except US): KOLYNOS DO BRASIL LTDA. [BR/BR]; Rua Alexandre Dumas, 2200, 3 andar, Chacara Santo Antonio, CEP-04717-910 Sao Paulo, SP (BR). (72) Inventors; and (75) Inventors/Applicants (for US only): SUHONEN, Christopher [US/US]; 6640 Fair Oaks Drive, Alto, MI 49302 (US). FONTANA, Jose, E. [BR/BR]; Apartamento 34B, Rue Capitaes Mores, 93, CEP-03167-030 Sao Paulo, SP (BR). (74) Agent: McGREAL, Michael, J.; Colgate-Palmolive Company, 909 River Road, P.O. Box 1343, Piscataway, NJ 08855-1343 (US).</p>	<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</p>	
<p>(54) Title: DENTAL FLOSS</p> <p>(57) Abstract</p> <p>The nylon fiber strand is coated with a coating to produce a coated surface on the nylon that mimics the surface characteristics of polytetrafluoroethylene (PTFE). The coating is comprised of a base prime coat and a top finish coat. These coatings are applied separately to the nylon fiber strand. The top finish coat which is also known as the nylon wax coat is comprised of waxes, an ester and a silicone, and primarily of waxes. The waxes are comprised of a mixture of a low melting point wax and a high melting point wax.</p>		

THIS PAGE BLANK (USFTO)

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DENTAL FLOSS

Field of the Invention

5

This invention relates to a dental floss that can be readily gripped and which can be readily inserted into close interdental spaces. More particularly, this invention relates to a tape type of dental floss that has a
10 coating that increases the lubricity of the base fiber to make it easier to use.

Background of the Invention

15 A well-recognized problem with regard to flosses, whether they are tape flosses or multifilament flosses, is the catching on tooth surfaces during movement into and through close contact interdental spaces. In some instances the floss will break and shred and parts of the floss will become stuck between the teeth. It then takes more flossing to remove floss
20 segments from between one's teeth. This has been a continuing problem which is solved through the use of the new polytetrafluoroethylene (PTFE) fiber flosses. However, PTFE is a relatively expensive fiber. Therefore, it has been an objective to provide a fiber that has the ease of use characteristics of PTFE while using a lower cost fiber. This can be the
25 result of forming a particular fiber composition or it can be by providing a coating on a non-PTFE fiber that makes the non-PTFE fiber mimic a PTFE fiber in use as a floss. Since a PTFE fiber has a low coefficient of friction (COF), it inherently readily passes into close interdental spaces.

30 PTFE flosses are disclosed in U.S. Patent 5,033,488 and U.S. Patent 5,209,251. These consist of one or more strands of expanded PTFE

with a wax or other coating to increase the grippability of the fiber in use as a floss. A microcrystalline wax was found to be one effective wax. However, other coatings that adhere to PTFE, that are not brittle at about room temperature and which have a melting point above 50°C can be used.

5 The coating will raise the COF of the expanded PTFE above about .08. A wax coated non-PTFE fiber floss is disclosed in U.S. Patent 4,996,056. In this patent there is disclosed a nylon, polyester or polypropylene fiber that is coated with solid particles of a fluoropolymer in a binder. The binder can be a wax or a non-wax, with a wax being preferred. The fluoropolymer
10 particles can be PTFE particles of a particle size of about 1 to 50 millimicrons. European Patent Application 423 541 A2 discloses formulations for coating flavorants and other materials onto PTFE surfaces, including flosses.

15 These patent publications set out the present state of the art of flosses that contain PTFE. The expanded PTFE fiber flosses slip easily into tight interdental spaces. However, expanded PTFE film can cost 3 to 10 times the cost of other fibers. Although a useful floss fiber, it is expensive. The non-PTFE fiber coated with particulate PTFE is not a low COF floss.
20 This is the case since the PTFE particle coating is scrapped from the fiber during insertion between the teeth and the subsequent motion of the floss. The full benefits of a PTFE fiber then are no longer achieved.

Waxes have been coated onto conventional floss fibers for many
25 years. Although microcrystalline waxes are the most commonly used waxes, other waxes, such as beeswax, paraffin waxes, carnauba wax and polyethylene wax can also be used. The floss fibers are usually nylon, however, other fibers such as polyethylene, polypropylene, polyester, cellulose and cotton also are used. The wax coating lubricates the fiber so
30 that it can more easily slip into tight interdental spaces and also serves as a

binder for multifilament flosses. However, none of these coatings onto these floss fibers have proven to impart to the non-PTFE fibers the characteristics of PTFE flosses. The objective is to use a lower cost conventional fiber and to achieve the surface lubricity of PTFE.

5

Brief Summary of the Invention

It has been found that non-PTFE fibers such as nylons, polyenes such
10 as polyethylene, polypropylene and polybutadiene, polyesters, ethylene-propylene copolymers, ethylene-vinyl acetate copolymers, ethylene vinyl alcohol copolymers, and cellulotics can be coated so that they can gain at least some of the surface characteristics similar to those of PTFE. The usual PTFE flosses are in the form of a tape. They usually are of about 800
15 to 1500 denier prior to any coating. A non-PTFE fiber strand can be made to mimic many of the surface characteristics of PTFE by the application of a two-stage coating. The non-PTFE fiber strand is first coated with a nylon bonding coating and then with a wax coating. The nylon bonding coat is in the nature of a primer coat. The wax coat is the coating which is to
20 duplicate as much as possible the desirable properties of PTFE. The overall coating level of the two coatings onto the fiber strand is about 12% to 22% by weight. The ratio of the wax coating to the nylon bonding coating is about 1:1 to about 3:1.

25 The two-stage coating process produces a non-PTFE fiber strand that has the lubricious surface characteristics of PTFE. The strand slips readily between teeth, including teeth with tight interdental spaces. The coated strand also is easy to grip for flossing. The fiber strand does not slip from between a person's fingers when the strand gets caught between two closely
30 spaced teeth.

Detailed Description of the Invention

5 It has been found that a non-PTFE fiber strand can be produced that has surface characteristics similar to many of those of PTFE. That is, it has a lubricious surface that mimics the surface of PTFE in use as a floss. A preferred film strand is nylon and the invention will be described with regard to nylon but with the understanding that other films will be used.

10 The nylon fiber strand can be a monofilament strand or a multifilament strand. It will have a denier of about 300 to 2000 denier. The nylon bonding coat is comprised of a polyamide solution, a silicone, PTFE resin powder and an alcohol as the solubilizing and application
15 vehicle. The formulation contains about 10% to about 20% of the polyamide solution, and preferably about 15% by weight. The silicone is present in an amount of about .5% to about 3% by weight, and preferably about 1.5%. The PTFE resin powder is present in an amount of about 0.2% to about 1% by weight, and preferably about 0.5%. The remainder is alcohol carrier and
20 solubilizing vehicle which alcohol usually is ethanol.

The wax coat is comprised of waxes, along with glycerol esters and silicones. Preferably the waxes are comprised of a mixture of a low melting point wax and a high melting point wax. A low melting point wax is a wax
25 that has a melting point between about 50°C and 65°C. A high melting point wax is a wax that has a melting point above about 75°C. The coating also includes a glycerol ester, such as glycerol triacetate, and a silicone.

The silicone preferably is a silicone copolymer. The silicone provides the formulation which creates a silky, slippery surface effect on the fiber surface. Suitable silicone copolymers are organosilicones.

5 The waxes comprise about 80% to about 96% by weight of the formulation. The low melting point wax is present in a ratio of about 1:1 to about 2:1 of the high melting point wax. The glycerol ester is present in an amount of about 5% to about 10% by weight with the silicone being present in an amount of 1% to 3% by weight. The preferred glycerol ester is glycerol
10 triacetate. The preferred silicone is a silicone copolymer such as methylalkyl polysiloxane copolymer.

The nylon bond coating is put into the nylon in a first step. This can be put onto the nylon strand using essentially any coating technique.
15 These include lick roll, submersion and squeeze rolls and spraying. After coating, the fiber strand is heated to remove the ethanol. The fiber strand then is coated with the wax coat. This wax coat can be put onto the fiber by any of the above mentioned techniques.

20 The overall coating level on the fiber strand is about 12% to about 22% by weight. The ratio of the wax coating to the nylon bond coating is about 1:1 to about 3:1.

EXAMPLE 1

25

A nylon fiber having a nominal 700 denier was coated with the nylon bonding coat and the wax coat. The nylon bonding coat is applied at a coating of 6.5 percent by weight and the wax coat is applied at a coating of 11 percent by weight at a total coating level of 17.5%. The coating is
30 applied by immersing the fiber into a bath containing the coating with the excess removed by a squeegee.

The coatings have the following compositions:

Nylon Bonding Coating

5	Polyamide Stock Solution	15% by weight
	Dimethicone Copolyol	1.5% by weight
	PTFE Resin Powder	0.5% by weight
	Ethanol	83.0% by weight

10 Wax Coating

	Low-melting Point Wax	53% by weight
	Beeswax	38% by weight
	Glycerol Triacetate	7% by weight
	Silicone Copolymer	2% by weight

15

The coated nylon fiber has a denier of 873 and a break strength of 45 Newtons. The relative friction is greater than PTFE flosses but less than commercially available wax coated nylon fibers.

Claims

What is claimed is:

- 5 1. A dental floss comprising a non- PTFE fiber having a denier of about 300 to 2000 and coated with a first coating and a second coating, said second coating overlaying said first coating, said first coating being a nylon bonding coating and said second coating being a wax coating.
- 10 2. A dental floss as in claim 1 wherein said first coating is comprised of a polyamide solution, a silicone and PTFE resin powder in an alcohol solubilizing vehicle.
- 15 3. A dental floss as in claim 2 wherein said polyamide is present in about 10% to about 20% of the polyamide solution by weight, the silicone is present in about 0.5% to about 3% by weight, the PTFE resin powder is present in an amount of about 0.2% to about 1% by weight, the remainder being said alcohol solubilizing vehicle.
- 20 4. A dental floss as in claim 1 wherein said wherein said second coating is primarily a wax coating.
5. A dental floss as in claim 4 wherein said wax coating contains at least one glycerol ester and at least one silicone.
- 25 6. A dental floss as in claim 4 wherein said wax is a mixture of a first wax having a melting point of between about 50°C and about 65°C and a second wax having a melting point of more than about 75°C.

7. A dental floss as in claim 6 wherein said first wax is present in a ratio of about 1:1 to about 2:1 of said second wax.
8. A dental floss as in claim 4 wherein said wax comprises about 80% to about 96% by weight of said second coating.
9. A dental floss as in claim 8 wherein said glycerol ester is present in an amount of about 5% to about 10% by weight of said second coating.
10. A dental floss as in claim 9 wherein said silicone is present in an amount of about 1% to about 3% by weight of said second coating.
11. A dental floss wherein the ratio of aid first coating to said second coating is about 1:1 to about 3:1.
12. A dental floss as in claim 1 wherein the coating of said first coating and said second coating on said non-PTFE fiber is about 12% to about 22% by weight of said floss.
13. A dental floss as in claim 1 wherein said non-PTFE fiber is selected for the group consisting of nylons, polyenes polyesters, ethylene-propylene copolymers, ethylene-vinyl acetate copolymers, ethylene vinyl alcohol copolymers and cellulose.
14. A dental floss as in claim 13 wherein said non-PTFE fiber is a nylon.
15. A dental floss as in claim 4 wherein said wax is selected from the group consisting of microcrystalline waxes, beeswax, paraffin waxes, carnauba wax and polyethylene waxes.

16. A dental floss comprising a non-PTFE fiber having a first coating and a second coating, said first coating comprising primarily a polyamide dispersed in an alcohol carrier and said second coating comprising primarily a wax coating, said first coating being in a ratio of about 1:1 to about 3:1 of said second coating, said first coating and said second coating being in a content of about 12% to about 22% of said floss.
17. A dental floss as in claim 16 wherein said first coating further contains a silicone and particulate PTFE and said second coating further contains a glycerol ester and a silicone.
18. A dental floss as in claim 16 wherein said wax is comprised of a first wax having a low melting point and a second wax having a high melting point.
19. A dental floss as in claim 18 wherein said first wax is in a concentration of about 1:1 to about 2:1 to said second wax.
20. A dental floss as in claim 16 wherein said non-PTFE fiber is a nylon.

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61C15/04 A61K7/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61C A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 93 02633 A (GILLETTE) 18 February 1993 see the whole document ---	1,4, 13-16,20
A	WO 91 08792 A (WHITEHILL) 27 June 1991 see claim 2 ---	1,5
A	US 4 996 056 A (BLASS) 26 February 1991 cited in the application see the whole document -----	1,4



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier document but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
 "&" document member of the same patent family

Date of the actual completion of the international search

30 March 1999

Date of mailing of the international search report

08/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Vanrunxt, J

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9302633 A	18-02-1993	US 5226435 A	13-07-1993
		AT 173387 T	15-12-1998
		AU 663107 B	28-09-1995
		AU 2412292 A	02-03-1993
		BR 9206322 A	04-04-1995
		CA 2114415 A	18-02-1993
		DE 69227631 D	24-12-1998
		EP 0597005 A	18-05-1994
		EP 0836837 A	22-04-1998
		EP 0832615 A	01-04-1998
		MX 9204484 A	01-02-1993
		US 5357990 A	25-10-1993
WO 9108792 A	27-06-1991	AT 149360 T	15-03-1997
		DE 69030105 D	10-04-1997
		DE 69030105 T	12-06-1997
		DK 506659 T	15-09-1997
		EP 0506659 A	07-10-1992
		ES 2100889 T	01-07-1997
		US 5165913 A	24-11-1992
US 4996056 A	26-02-1991	EP 0358363 A	14-03-1990
		JP 2167155 A	27-06-1990

THIS PAGE BLANK (USPTO)